

PRODUCT DATA SHEET

SikaGrout[®]-280 HS

HIGH PRECISION, IRON AGGREGATE AND MICRO FIBRE REINFORCED, NON-SHRINK CEMENTITIOUS GROUT

DESCRIPTION

A non-shrink, cementitious premixed grout with iron aggregate and micro fibre to provide excellent impact and vibration resistance.

USES

For grouting over a wide range of applications:

- Machine bedding/base plates
- Turbine - generator set base plates
- Centrifugal compressors
- Crane rails
- Crusher – Ball Mills
- Structure that has high vibration

CHARACTERISTICS / ADVANTAGES

- Easy to use, just add water
- Good flow characteristic.
- Adjustable consistency.
- Rapid strength development.
- Highly improved Impact and vibration resistant compared to conventional cementitious grout
- Shrinkage compensated.
- High final strength.
- Non-Toxic.

PRODUCT INFORMATION

Packaging	25 kg bag
Appearance / Colour	Powder / Grey
Shelf Life	9 months from date of production if stored in undamaged and unopened original sealed bags
Storage Conditions	Stored in dry condition between 10 °C - 30 °C
Density	~2.28 kg/L

TECHNICAL INFORMATION

Compressive Strength	1 day	~40.0 N/mm ²	(ASTM C-349)
	3 days	~60.0 N/mm ²	
	7 days	~73.0 N/mm ²	
	28 days	~88.0 N/mm ²	
Tensile Strength in Flexure	1 day	~8.0 N/mm ²	(ASTM C-348)
	3 days	~12.5 N/mm ²	
	7 days	~16.0 N/mm ²	
	28 days	~20.0 N/mm ²	

Expansion	at 27 °C	0.05 %	(ASTM C-940)
Tensile Adhesion Strength	28 Days	~1.5 N/mm ² (Concrete failure, over mechanically roughened concrete surface)	
	28 Days	~2.5 N/mm ² (Over mechanically roughened grout surface)	

APPLICATION INFORMATION

Mixing Ratio	4.0 L per 25 kg bag (water per powder = 16 % by weight)		
Consumption	~1 970 kg/m ³ of mortar.		
Yield	12.70 L per 25 kg bag		
Layer Thickness	Recommended thickness is 20 - 150 mm		
Flowability	Flowable (mm)	>200	(Flowtable)
Product Temperature	< 30 °C, max		
Ambient Air Temperature	10 °C - 35 °C		
Substrate Temperature	10 °C - 35 °C		
Pot Life	25 min		
Setting Time	Initial Setting Time (at 27 °C)	~5 - 8 h	
	Final Setting Time (at 27°C)	~6 - 9 h	

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

SURFACE PREPARATION

- Remove dirt, oil, grease, loose material and other bond-inhibiting materials.
- Anchor bolts to be grouted must be degreased with suitable solvent.
- Concrete must be sound and roughened to promote mechanical adhesion.
- Prior to pouring, surface must be wetted to saturated surface dry.

FORMING

For flowable grout, construct forms to retain grout without leakage. Formwork should be lined or coated with bond-breaker for easy removal. Formwork should be able to accommodate head of grout.

MIXING

Put appropriate quantity of water (depend on the required consistency) into a mixing vessel. Add slowly the total contents of SikaGrout®-280 HS while mixing. Mix continuously for 3 minutes to achieve an even consistency. Use a mechanically low speed drill (400–600 rpm) with mixing paddle or suitable pan mixer.

APPLICATION

Within 25 minutes after mixing, place grout into forms one side to avoid air entrapment. Do not vibrate. Use a suitable head box of 150–200 mm and maintain the grout head at all times to ensure a continuous flow. Gentle tapping or pulling loops of wire from one side may assist the flow of the mortar under difficult working conditions.

CURING TREATMENT

Wet cure for a minimum of 3 days with wet hessian, plastic sheet or apply a curing compound (Antisol).

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened and / or cured material can only be remove mechanically.

LIMITATIONS

- Minimum applications thickness : 20 mm.
- Recommended thickness of SikaGrout® 280 HS in one pour is 20 mm to 150 mm. If the application thickness exceeds 150 mm, special procedure must be taken to anticipate temperature rise.
- Variations in cement could cause shade differences in colour of the mortar.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

PT. Sika Indonesia

Jl. Raya Cibinong-Bekasi km.20.

Cileungsi, Bogor 16820 - Indonesia

Tel. +62 21 8230025

Fax. +62 21 8230026

Website: idn.sika.com

email: sikacare@id.sika.com



SikaGrout-280HS_en_ID_(09-2016)_1_2.pdf

Product Data Sheet
SikaGrout®-280 HS
September 2016, Version 01.02
020201010010000127